

L Number	Hits	Search Text	DB	Time stamp
1	75	(pyrolytic with boron with nitride) and (428/\$.ccls. 220/\$.ccls.)	USPAT	2003/04/24 09:16
2	26	(pyrolytic with boron with nitride) and (428/\$.ccls. 220/\$.ccls.) and (crucible container)	USPAT	2003/04/24 10:26
3	5	(pyrolytic with boron with nitride) and (428/\$.ccls. 220/\$.ccls.) and (crucible container) and (dope doping dopant)	USPAT; EPO; JPO; DERWENT	2003/04/24 10:49
4	30	(pyrolytic with boron with nitride) same (crucible container) same (dope doping dopant)	USPAT; EPO; JPO; DERWENT	2003/04/24 11:00
5	15	(pyrolytic with boron with nitride) same (crucible container) same susceptor	USPAT; EPO; JPO; DERWENT	2003/04/24 11:03
6	12	(pyrolytic with boron with nitride) and (inner with outer with crucible) and (heat heating heated) and (doping dopant doped)	USPAT; EPO; JPO; DERWENT	2003/04/24 11:50
7	35	(pyrolytic with boron with nitride) and (inner with outer with crucible) and (heat heating heated)	USPAT; EPO; JPO; DERWENT	2003/04/24 11:57
8	23	"5158750"	USPAT; EPO; JPO; DERWENT	2003/04/24 11:35
9	12	("1475650" "1709729" "1721994" "3345059" "3986822" "4058579" "4090851" "4264803" "4446357" "4596700" "4613306" "4773852").PN.	USPAT	2003/04/24 11:36
12	21	(boron with nitride) and (inner with outer with crucible) and (heat heating heated) and (doping dopant doped)	USPAT; EPO; JPO; DERWENT	2003/04/24 11:50
13	0	(pyrolytic with boron with nitride) and (inner with outer with crucible) and (light with (absorbing absorbed absorption))	USPAT; EPO; JPO; DERWENT	2003/04/24 11:58
14	21	(pyrolytic with boron with nitride) and (light with (absorbing absorbed absorption))	USPAT; EPO; JPO; DERWENT	2003/04/24 11:58